

## DENSO ULTRASEAL RT TAPE

### DESCRIPTION

Denso Ultraseal Reinforcing Tape (Ultraseal RT) is designed for use as an outer armouring for Densyl or Denso Petrolatum Tapes. Ultraseal RT Tape is spirally applied and the coated with Denso Acrylic Topcoat or a **solvent free** Epoxy (Denso ST100) which quickly sets to form a tough UV resistant outer armouring. Denso RT Tape can also be used in the following applications:

- *Flashings and profile copings on all types of roofs.*
- *Side and end laps on asbestos and metal roofs.*
- *General roof repairs.*
- *Parapet wall capping.*
- *Tankbase protection.*

### COMPOSITION

The membrane consists of a non-woven synthetic fibre fabric laminated to a pressure sensitive, modified bitumen compound. The rolls are interleaved with a disposable release film.

### SAFETY

Normal hygiene procedures. Wash hands thoroughly with soap and water or a proprietary hand-cleaner prior to eating or smoking. Launder contaminated clothing, gloves, etc.

### STORAGE

Store in original containers in a cool dry place. Maximum recommended shelf life : 6 months.

**DENSO ULTRASEAL RT TAPE (cont.)**

TYPICAL PROPERTIES	TEST METHOD	DATA
<b>Breaking Strength</b>	ASTM D1000	2N/mm
<b>Elongation @ Break</b>	ASTM D1000	100%
<b>Adhesion</b>		
- To Primed Steel	ASTM D1000	2.5N/mm
- To Self	ASTM D1000	2.0N/mm
<b>Resistance to Acids, Alkalis &amp; Salts</b>		Excellent
<b>Temperature Range</b>		
- For Application		+15°C to 45°C
- For Service		+5°C to 65°C
<b>Length</b>		15m
<b>Width</b>		100, 175 & 275mm (or to order)
<b>Core Size</b>		76mm I.D
<b>Thickness</b>	ASTM D1000	1100µm
<b>Weight</b>		1.20Kg/m <sup>2</sup>
<b>Recommended Primer</b>		Denso Bitumen Primer D

**Important**

Winn & Coales / Denso SA (Pty) Ltd pursue a policy to develop and continually improve all of our products and therefore the information given in this data sheet is intended as a general guide and does not constitute a warranty of specification. However, our sales personnel are committed to assist the user in establishing the suitability of the product for its intended purpose and additional specific information is available on request.

Denso SA (Pty) Ltd operate a Quality Management System registered to ISO 9001:2008).

Head Office / Factory: 120 Malacca Road, Red Hill, Durban. P.O.Box 201259, Durban North, 4016, South Africa

Tel: +27 (031) 569 4319 Fax: +27 (031) 569 4328 Email: bid@denso.co.za Website: www.denso.co.za