



DENSO D14 SCRIM

DESCRIPTION	Denso D14 Scrim saturates easily and is used as a reinforcement in conjunction with Denso protective coatings, e.g. Denso Basecoat Kit, Denso Acrylic Topcoat, etc.
COMPOSITION	A non-woven membrane with longitudinal reinforcing stitching, manufactured from 100% polyester fibres.
SAFETY	Normal hygiene procedures. Wash hands thoroughly with soap and water or a proprietary hand-cleaner prior to eating. Launder contaminated clothing, gloves, etc.
STORAGE	Store in original containers in a cool, dry place away from and sources of ignition. Recommended shelf life: 12 months

TYPICAL PROPERTIES	TEST METHOD	DATA
Breaking Strength	ASTM D1000	200N/50mm minimum
Elongation @ Break	ASTM D1000	25% average
Roll Length		20m (other lengths to order)
Width		50-300mm
Weight		100g / m ²
Thickness	ASTM D1000	900µm

Important

Winn & Coales / Denso SA (Pty) Ltd pursue a policy to develop and continually improve all of our products and therefore the information given in this data sheet is intended as a general guide and does not constitute a warranty of specification. However, our sales personnel are committed to assist the user in establishing the suitability of the product for its intended purpose and additional specific information is available on request.

Denso SA (Pty) Ltd operate a Quality Management System registered to ISO 9001:2008.

Head Office / Factory: 120 Malacca Road, Red Hill, Durban. P.O.Box 201259, Durban North, 4016, South Africa
Tel: +27 (031) 569 4319 Fax: +27 (031) 569 4328 Email: bid@denso.co.za Website: www.denso.co.za