

## **DENSO MASTIC BLANKETS**

<b>DESCRIPTION</b>	Performed cross sections of Denso Mastic, extruded or moulded onto a backing of Denso Petrolatum Tape. This structure provides extra support and allows fast application to fixtures and fittings.
<b>USES</b>	Used for the contouring of flanges, couplings, valves and irregular surfaces. The blankets are used in conjunction with the appropriate primer, petrolatum tape and outerwrap suite to the particular requirements of each individual contract.
<b>FEATURES</b>	<ul style="list-style-type: none"><li>➤ Fast easy application over wide temperature range</li><li>➤ Minimal surface properties</li><li>➤ Inert and environmentally stable</li><li>➤ Contains no VOCs</li><li>➤ Unaffected by water, mineral acids, alkalis and salts</li></ul>
<b>APPLICATION</b>	Steel surfaces should be prepared to a minimum of ST2. The cleaned surface is primed with the appropriate primer, then the mastic blanket is moulded by hand to fill irregular shapes and reduce sharp edged surfaces.
<b>SAFETY</b>	Normal hygiene procedures. Wash hands thoroughly with soap and water or a proprietary hand-cleaner prior to eating. Launder contaminated clothing, gloves, etc.
<b>STORAGE</b>	Store in original containers in a cool, dry place away from and sources of ignition. Recommended shelf life: 6 months



LEADERS IN CORROSION PREVENTION AND SEALING TECHNOLOGY

# TECHNICAL DATA SHEET

OVER 130 YEARS SERVICE TO INDUSTRY



ISO 9001:2008 Certified

Document Reference: TDS169 B Rev: 01

TYPICAL PROPERTIES	DATA
<b>Colour</b>	Dull cream
<b>Specific Gravity</b>	0.72
<b>Flash Point</b>	>180°C
<b>Solids Content</b>	100%
<b>Temperature Range</b> <i>For Application</i> <i>For Service</i>	0°C to 45°C 60°C maximum
<b>Nominal Thickness</b>	10-12mm
<b>Available sizes</b>	1.1m x 250mm 750mm x 250mm 500mm x 250mm

**Important**

Winn & Coales / Denso SA (Pty) Ltd pursue a policy to develop and continually improve all of our products and therefore the information given in this data sheet is intended as a general guide and does not constitute a warranty of specification. However, our sales personnel are committed to assist the user in establishing the suitability of the product for its intended purpose and additional specific information is available on request.

Denso SA (Pty) Ltd operate a Quality Management System registered to ISO 9001:2008.

Head Office / Factory: 120 Malacca Road, Red Hill, Durban. P.O.Box 201259, Durban North, 4016, South Africa

Tel: +27 (031) 569 4319 Fax: +27 (031) 569 4328 Email: bid@denso.co.za Website: www.denso.co.za