

## **DENSO MASTIC SEALING TAPE**

### **DESCRIPTION**

Typically used in the following applications:

- General double sided adhesive tape
- To seal weldbeads on steel pipelines prior to the overwrapping with an appropriate Denso corrosion protection tape system.
- To seal the sides and end laps on metal roof cladding to form an impervious barrier against the ingress of dust and moisture. (See Cladseal 1500 data sheet)
- Fixing of temporary road studs.

### **COMPOSITION**

A highly conformable, non-hardening, pressure-sensitive compound, based on a polymer modified bitumen and tackifying resins.

The compound is extruded in the form of a double sided tape and, due to its tenacious adhesiveness, the tape in supply form is sandwiched between a disposable release film.

### **SAFETY**

Normal hygiene procedures. Wash hands thoroughly with soap and water or a proprietary hand-cleaner prior to eating or smoking. Launder contaminated clothing, gloves, etc.

### **STORAGE**

Store in original containers in a cool dry place. Maximum recommended shelf life : 6 months.



LEADERS IN CORROSION PREVENTION AND SEALING TECHNOLOGY

# TECHNICAL DATA SHEET

OVER 130 YEARS SERVICE TO INDUSTRY



ISO 9001:2008 Certified

Document Reference: TDS276 Rev: 01

TYPICAL PROPERTIES	TEST METHOD	DATA
<b>Adhesion</b> <ul style="list-style-type: none"><li>- To Primed Steel</li><li>- To Self</li></ul>	ASTM D1000 24hr ASTM D1000 24hr	2.5N/mm 2.5N/mm
<b>Resistance to Acids, Alkalis &amp; Salts</b>		Excellent
<b>Temperature Range</b> <ul style="list-style-type: none"><li>- For application</li><li>- For Service</li></ul>		+15°C to 45°C +10°C to 65°C
<b>Length</b>		7.5m
<b>Width</b>		75mm, 150mm (or to order)
<b>Core Size</b>		76mm I.D
<b>Thickness</b>		1500µm
<b>Weight</b>		1.5Kg/m <sup>2</sup>
<b>Recommended Primer</b>		Denso Bitumen Primer D

**Important**

Winn & Coales / Denso SA (Pty) Ltd pursue a policy to develop and continually improve all of our products and therefore the information given in this data sheet is intended as a general guide and does not constitute a warranty of specification. However, our sales personnel are committed to assist the user in establishing the suitability of the product for its intended purpose and additional specific information is available on request.

Denso SA (Pty) Ltd operate a Quality Management System registered to ISO 9001:2008.

Head Office / Factory: 120 Malacca Road, Red Hill, Durban. P.O.Box 201259, Durban North, 4016, South Africa  
Tel: +27 (031) 569 4319 Fax: +27 (031) 569 4328 Email: bid@denso.co.za Website: www.denso.co.za