

DENSO MDP 032 TAPE

DESCRIPTION Denso MDP 032 Tape is used as a protective outerwrap over Denso Pipeline Innerwrap Taping systems in buried applications. Not recommended as outer wrap for exposed / above ground applications.

- High impact strength.
- Low permeability to oxygen and moisture vapour.
- Excellent electrical resistance.
- Resistant to all common acids, alkalis and salts normally found in soils.

COMPOSITION A white medium density polyethylene film, coated with a pressure sensitive adhesive.

SAFETY Normal hygiene procedures. Wash hands thoroughly with soap and water or a proprietary hand-cleaner prior to eating or smoking. Launder contaminated clothing, gloves, etc.

STORAGE Store in original containers in a cool, dry place. Recommended shelf life: 6 months
Wrapped pipe / fittings should not be left exposed to direct sunlight for longer than fourteen (14) days.

TYPICAL PROPERTIES	TEST METHOD	DATA
Tensile Strength	ASTM D1000	15 Mpa min
Elongation at break	ASTM D1000	>350%
Thickness	ASTM D1000	
• Backing film		300µ
• Adhesive		20µ
Adhesion to self	ASTM D1000	0.04N/mm
Dielectric strength	ASTM D1000	20Kv min
Roll Widths	ASTM D1000	50mm, 75mm, 100mm, 150mm (or to order)
Roll Length	ASTM D1000	50m (or to order)
Colours		White

Important

Winn & Coales / Denso SA (Pty) Ltd pursue a policy to develop and continually improve all of our products and therefore the information given in this data sheet is intended as a general guide and does not constitute a warranty of specification. However, our sales personnel are committed to assist the user in establishing the suitability of the product for its intended purpose and additional specific information is available on request.

Denso SA (Pty) Ltd operate a Quality Management System registered to ISO 9001:2008.

Head Office / Factory: 120 Malacca Road, Red Hill, Durban. P.O.Box 201259, Durban North, 4016, South Africa
Tel: +27 (031) 569 4319 Fax: +27 (031) 569 4328 Email: bid@denso.co.za Website: www.denso.co.za