

## **DENSO JOINT SEALER**

Pressure Sensitive, Non-Hardening Bitumen Compound Strips

### **DESCRIPTION & COMPOSITION**

A pressure-sensitive compound comprising of a blend of selected bitumens, synthetic elastomeric polymers and tackifying resins. The compound is supplied in the form of strips of triangular cross section.

### **USES**

The primary use of the Joint Sealer is for the permanent sealing of the joints between the precast manhole sections. It can also be used for the profiling of angled joints.

- Non-hardening
- Easily installed
- Stable over a wide temperature range
- Unaffected by water, mineral acids, alkalis and salts

### **SAFETY**

Normal hygiene procedures. Wash hands thoroughly with soap and water or a proprietary hand-cleaner prior to eating. Launder contaminated clothing, gloves, etc.

### **STORAGE**

Store in original containers in a cool, dry place away from and sources of ignition.

<b>TYPICAL PROPERTIES</b>	<b>TEST METHOD</b>	<b>DATA</b>
<b>Colour</b>		Black
<b>Specific Gravity</b>		1.0
<b>Solids Content</b>		100%
<b>Adhesion</b> <i>To Primed Concrete @ 25°C</i>		Good
<b>Elongation at Break</b>		600%
<b>Acid, Alkali &amp; Salt Resistance</b>		Excellent
<b>Temperature Range</b> <i>For Application &amp; Service</i>		15°C to +65°C
<b>Strip Profile</b>		Approx. 18mm Triangular Strips x 1.1m long (V Belt Shape)
<b>Packaging</b>		30 strips per box

#### ***Important***

*Winn & Coales / Denso SA (Pty) Ltd pursue a policy to develop and continually improve all of our products and therefore the information given in this data sheet is intended as a general guide and does not constitute a warranty of specification. However, our sales personnel are committed to assist the user in establishing the suitability of the product for its intended purpose and additional specific information is available on request.*

*Denso SA (Pty) Ltd operate a Quality Management System registered to ISO 9001:2008.*

Head Office / Factory: 120 Malacca Road, Red Hill, Durban. P.O.Box 201259, Durban North, 4016, South Africa

Tel: +27 (031) 569 4319 Fax: +27 (031) 569 4328 Email: bid@denso.co.za Website: www.denso.co.za